



TECHNICAL DATA SHEET
WETSUIT® 2-Part
17-WS-55



Register 14499



CODEMARK®
BCS-140615-CMNZ
BCS-CM60001



APPROVED

#3030656

Wetsuit® 2-Part Fluid Applied Membrane Professional Use Only

DESCRIPTION

WetSuit® 2 Part is a patented VOC-Free, instant-set, water-based two-component cold spray applied, fully-adhered, auto-terminating bituminous high grade rubber membrane suitable for a variety of waterproofing, roofing, air/vapor barrier, and protective applications. WetSuit® 2 Part builds to any millage in a single pass application resulting in rapid application and a variety of vertical and horizontal uses

RECOMMENDED USE

WetSuit® is designed for exterior and interior vertical and horizontal waterproofing, roofing, and environmental barrier applications. Typical applications include:

Split slab and structural slab waterproofing	Plaza decks, balconies, roof decks
Sea walls, dams and retaining walls	Green roofs, blue roofs, terraces, and planters
Corrosion protection, wall restoration	Below grade foundations and walls
Impermeable air and vapor barriers	Ponds, fountains, pools, tanks, containment
Marine and industrial applications	New and retrofit roofing over Capsheet/APP, Single-Ply (TPO, PVC, EPDM), metal roofs, built-up roofs, plywood, spray foam, and many coatings

FEATURES AND BENEFITS

- Single pass application for any millage with uniform composition and no mud-cracking or pin-holing; 1,500 sqft/hour- 140 sqm/ hour with a 3 men crew spray rate achievable and wide variety of uses
- Versatile: proven in waterproofing, roofing, and air/vapor barrier applications, hydrostatic and dry, exposed and buried, interior and exterior, vertical and horizontal
- Durable: 2124% elongation and superb memory, highly resistant to puncture and impact, approved for foot traffic, excellent weathering performance, withstands ponding water indefinitely and is Class A Fire Rated and self extinguishing
- Simple: High adhesion with the waterbased Wetsuit® primer over a wide variety of substrates eliminates laborious prep; system is easy to clean and components mix externally
- True waterproofing performance.
- Accelerated spray is 80% cured in 3 Seconds—immediately tack free
- Environmentally friendly, low-impact install; LEED eligible
- Simple prep work, Require fabric reinforcement only on gap, transitions and joints, no torches or melting pots



CERTIFICATIONS

	Codemark New-Zealand for roofing	Certificate # BCS-140615-CMNZ
	Codemark Australia for Roofing	Certificate # BCS-CM60001
	FM Approval Class 1 roofing - FM 4470 ASTM E108 Wind uplift Hail Damage Foot Traffic. Leakage susceptibility	Certificate # 3030656 Class A on 2 in 12 Slope Class 1-990 on Concrete Class 1-420 on Mod Bitumen Class Severe Hail (SH) Passed Passed
	Florida Building Code compliance - 2014	Registration # 14499.1
	CE Mark Reaction to Fire Crack bridging Ability Resistance to rain Water resistance Flexibility at low temperature Dimensional stability at high temperature Reduction of layer thickness when fully dried Water tightness Resistance to compression	Notified Body 1119 - DOP-WS16001-E Class E Class CB2 Class R3 Passed Passed Passed Passed Class W2B Class C2B
Fire classes	EN 13501-5 EN 13501-1 ASTM E108	Class BroofT1 Non combustible substrate - Pitch <20° Class BroofT2 All substrate - All Pitch Class BroofT3 Non combustible substrate - Pitch < 10° Class BroofT4 All substrate - Flat roofs Euroclass E substrate Euroclass A2-s1,d0 Class A on a slope of 2 in 12

TECHNICAL DATA SHEET

NEPTUNE COATINGS



PROPERTIES

Property	Test Method	Result
Color		Brown to Black
Volatile Organic Compounds		0%
Shelf Life		1 year
Dry weight		60 mils : 6oz/ft ²
Ignition / Flash temperature	ASTM D92	960°F / 516°C
Elongation / Elongation after 2000 Hrs weathering / Elongation at freezing	ASTM D412	2124% / 1602% / > 550%
Tensile Strength / tensile strength after 2000 Hrs Weathering	ASTM D412	363.2 Psi / 525 Psi
Cold temperature pliability	ASTM D2136-02	Passed at -30°F
Water vapor Transmission (thickness 80 mils)	ASTM F1249-06	243 MNsg ⁻¹ / 0.072 perm
Puncture resistance (Blunt / Wedge)	ASTM D5635	80 J.in ⁻¹ / 21 J.in ⁻¹
Adhesion to concrete (before and after 2000 hrs weathering)	AS/NZ 1580.408.5	1.52MPa-221Psi / 1.92MPa-279Psi

PACKAGING / SHIPPING INFORMATION / STORAGE / TEMPERATURES

Container size	Shipping Class	Reference
55 Gallon drum (208.2 liters)	Class 55	17-WS-55

Mix periodically during storage (1x/Month)

One (1) WetSuit® 2-Part kit includes 50 gallon drum of coating and (1) bag of accelerator.

Store in a cool dry area between 40°F/5°C-90°F/32°C, Protect from freezing.

Temperature range for application : 40°F/5°C-100°F/38°C

COVERAGE

Application	Dry Thickness	SqFt/ Gal	l/Sqm
Air barrier	40 mil / 1 mm	24.86	1.64
Roofing	60 mil / 1.5 mm	16.57	2.46
Vertical waterproofing	80 mil / 2 mm	12.43	3.28
Horizontal Waterproofing	100 mil / 2.5 mm	9.94	4.10

Please, refer to specific coverage document.



SURFACE PREPARATION AND APPLICATION

WetSuit® should not be applied to wet surfaces or surfaces with latent moisture. Substrate temperature must be above 40°F/5°C, product must not be allowed to freeze during storage and until final cure. WetSuit® 2-Part is applied using Neptune Coatings patented WetSuit® Spray System. Spray System Technical Data Sheet for more information. Surface should be clean and dry with no oils, loose debris, laitance, organic matter or other interfering matter. See Neptune Coatings "Surface Preparation Quick Guide" for detailed substrate guidance, full application instructions in Guide Specifications.

TOP COATING AND SURFACE MODIFICATION

For a colored or reflective topcoat, use Neptune Coatings Reflex or approved equal. Contact manufacturer for approved coatings. For a granulated or bead finish, after the 2-Part membrane has been allowed to cure completely apply a 30 wet mil coat of WetSuit® 1-Part (single component) and broadcast approved bead or granule into it. Time to cure completely will depend on temperature and humidity conditions.

RE-APPLICATION

WetSuit® is self adhering, and does not require scarification. WetSuit® 1-Part or Trowel adhere directly to 2-Part. If a topcoat has been applied, contact Manufacturer.



CLEAN UP

Requires Pine-Sol (or equivalent) and water in a 5:1 mixture for flushing the equipment after the job. Equipment requires flushing if down me is greater than 72 hours.

SAFE PRACTICES

This product is designed for professional installation. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling. Information sources include but are not limited to SDS and product labels. More resources are available by contacting Neptune Coatings directly.

A painter's nose/mouth mask and goggles are recommended while spraying. Gloves are recommended to avoid minor skin irritation. Refer to SDS for complete safety information. We always recommend adherence to OSHA fall safety guidelines and best practices.

MINIMUM EQUIPMENT

Always use the specific Spraying system supplied by Neptune Coatings.

To our knowledge, all the technical information in this document is true and accurate at the date of publication of this technical data sheet and remain subject to modification without prior notice. The user can contact Neptune Coatings to verify the accuracy of the information before to specify the product or before to order it.

We warranty that our product are compliant with the standards of quality control established by Neptune Coatings. We don't accept any liability regarding the coverage ratio, the performances or any wound resulting from the use of the product. The responsibility of neptune Coatings if any is limited to the replacement of the product. No other warranty is given by Neptune Coatings directly or indirectly, by legal route or otherwise, regarding the suitability of the product to a given application.